

TECHNICAL DATA SHEET

HFP-VOC Series Polyester Basecoat

HFP-VOC Series Polyester Basecoat is a quick dry, good hiding, factory pack line of many popular colors. Various OEM colors are available. Ideal for overalls, large blend area repairs, or for ground-coat material. For a complete and current list of colors offered, please visit www.highteck.com.

HFP161C-1 is a transparent Pearl Coat. Before application it does require a base coat ground coat.

Application

Surface Preparation

For dry sanding, a final sanding step of P500-P600 grit is recommended using a maximum 100 grit step difference or less throughout the taken sanding steps. For wet sanding, a final sanding step of P800-P1000 grit is recommended using a maximum of 200 grit step difference or less throughout the sanding steps. Clean area with a good grade wax and grease remover and wipe dry with a clean cloth. Wipe area with tack cloth to remove any dust or dirt particles.

Mixing Directions

1 Part HFP-Series High Teck Basecoat

1 Part Reducer VOC-grade Universal Reducer <10% Hardener Basecoat Hardener (optional)

Spray Gun Set-up

Spray Gun: Fluid Tip: Application pressure:

Gravity feed 1.3-1.5mm 30 PSI at the spray gun air inlet

Gravity feed HVLP 1.3-1.5mm 10 PSI max at air cap

Siphon fees 1.6-1.8mm 40-50 PSI

Application

Apply 2 - 4 single coats or until full coverage is achieved.

Drying Schedule

Allow each coat to flash off for approximately 5 to 10 minutes at 70°F. Prior to clearcoat application, allow a minimum of 20 minutes flash time at 70°F and a maximum of 24 hours flash time at 70°F. Should this maximum time be exceeded, scuff surface and apply another coat.

Catalyst (Optional)

Can be catalyzed up to 10% of unreduced color portion with appropriate isocyanate hardener.

Cleaning of Equipment

Clean equipment with lacquer thinner.

Technical Data

Mixing Ratio
Pot life
Viscosity @ Gun
Recommended Film Thickness
Flash Point
Air Pressure @ Gun
Coverage @ 0.6 mil

VOC @ Gun

1:1 by vol. w/reducer Indefinite, if not catalyzed 13 - 15 sec #4 Zahn Appox. 0.4 - 0.8 mil 53°F TCC

30 PSI gravity feed, 10 PSI max at cap HVLP, 40-50 PSI siphon feed 286 sq ft/q

Maximum of 3.5 lb./gal in ready to spray form