


7350 Gray, 7355 Black Lacquer Primer Surfacers are high quality one component primer surfacers that are fast drying, easy sanding and fill quickly. 7350 Gray, 7355 Black provide great value for many applications.



DESCRIPTION

7350 - HIGH SOLIDS ACRYLIC LACQUER PRIMER SURFACER - GRAY

7355 - HIGH SOLIDS ACRYLIC LACQUER PRIMER SURFACER - BLACK



MIXING RATIO (2:3)

7350/7355 **TO** VOC Compliant Reducer
2 Parts 3 Parts



APPLICATION

Apply 1-3 full wet coats at 40-50 psi or (5-10 psi when using HVLP at the gun), allowing a 10-15 minute flash between coats.



DRY TIMES AT 77° F

FLASH TIME	5-10 MINUTES
TO SAND	30 MINUTES
TO DELIVER	30 MINUTES



RECOATING

7350/7355 may be recoated after a 30 minute dry at 77° F. After 8 hours dry time 7350/7355 must be sanded before topcoating.



POT LIFE

Not applicable.



FISH EYE

Do not use fish eye eliminator in this product.



PAINTING FLEXIBLE PARTS

Do not use flexible additives in this product.



EQUIPMENT CLEAN-UP

Clean equipment immediately after use with gun wash or a high quality lacquer thinner.



TECHNICAL DATA

Mixing Ratio: 2:3
Viscosity (RTS): 18 - 20 seconds #2 Zahn
Weight Solids (RTS): 20.58% - 27.09%
Volume Solids (RTS): 9.22% - 13.41%
Film Build: 0.8 mils per full wet coat
Coverage: 151 - 202 sq. ft. per gallon @ 1 dry mil

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
7350	4.5	542	4.2	502
7355	4.8	573	3.7	446
VOC Compliant Reducer	0.0	0	0.0	0
V.O.C. (RTS):				
7350/VOC Compliant Reducer	4.5	542	1.7	201
7355/VOC Compliant Reducer	4.8	573	1.5	178

Disposal/Safety: See MSDS for this product
Humidity Resistance: Excellent
Salt Spray Resistance: Excellent

NOTE: Products are not recommended for use in temperatures below 60° F. Use below these temperatures will effect dry times and performance. FOR INDUSTRY USE ONLY

Read MSDS Before Use

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.