



7210 High Solids Euro Clear is a quality 2:1 mix 2.1VOC Compliant European Clear Coat formulated for applications requiring a high gloss premium appearance. 7210 will dry to a glass like finish in air dry or forced dry applications. It has excellent weathering capability and is designed to resist stone chips and abrasions.


DESCRIPTION

7210 – 2.1VOC HIGH SOLIDS EURO CLEAR

7591 – FAST 2.1VOC 2K UNIVERSAL URETHANE ACTIVATOR


7592 – MEDIUM 2.1VOC 2K UNIVERSAL URETHANE ACTIVATOR

7593 – SLOW 2.1VOC 2K UNIVERSAL URETHANE ACTIVATOR



SURFACE PREPARATION

- 1) Clean surface using High Teck 7801V Wax and Grease Remover
- 2) Sand and prep surface to paint manufacturer's recommendations
- 3) Apply basecoat
- 4) Allow the final coat of basecoat to dry to manufacturer's recommendations
- 5) Just prior to spraying, remove any dust particles using an appropriate Tack Rag



MIXING RATIO (2:1)

2 Parts – 7210

1 Parts – 7591, 7592 or 7593

Reduce if necessary using High Teck 7770 (Fast), 7780 (Medium), or 7790 (Slow) Universal Zero VOC Reducer



APPLICATION

- 1) Apply 2-3 full wet coats of 7210 using a good quality spray gun with a 1.3-1.6mm tip.
- 2) Allow 10-15 minutes flash time between coats.
- 3) Allow 6-8 hours @ 68°F (20°C) air dry before polishing.



DRYING TIMES AT 68°F

Flash Time 10-15 Minutes

Time To Polish 6-8 Hours

FORCE DRYING AT 140°F

Flash Time 10-15 Minutes

Bake Time @ 140°F 30 Minutes

Or

Flash Time 10-15 Minutes

Infra Red Lamp 15 Minutes





RECOATING

7210 may be re-coated after a 30 minute dry time at 68°F(20°C).
After 8 hours dry time 7200 must sanded before re-coating.



POT LIFE

5 Hours @ 68°F (20°C)



FISH EYE

Do not use fish eye eliminator in this product.


PAINTING FLEXIBLE PARTS

Do not use flexible additives in this product.



EQUIPMENT CLEAN-UP

Clean equipment immediately after use with compliant solvent



TECHNICAL DATA

Gun Set-Up Gravity Feed

(HVLP) 1.3-1.6mm

Air Pressure @ Gun 8-10 psi

Conventional Pressure @ Gun 40-45 psi

V.O.C.

2.1 lbs/gal Sprayable 2:1 mix

39% Solids by Weight

Coverage Sq. Ft. / gal @ 1 mil

630 sq. ft. 2:1 mix

NOTE: Products are not recommended for use in temperatures below 60° F. Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY Read MSDS Before Use

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions. The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public

SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION