



## Description

7355 - HS Acrylic Lacquer Primer Surfacer - Black

Insert  
Product  
Image Here

7355 is a high quality lacquer primers that are easy to spray and sand, with good build and performance.



## Surface Preparation

1. Wash area thoroughly with soap and water to remove contaminates that solvent based cleaners cannot remove effectively.
2. Clean repair area with Wax and Grease Remover.
3. Completely sand surface with 180-220 grit paper and re-clean with a pre-paint cleaner.
4. For maximum adhesion and corrosion resistance, treat bare metal with a quality metal conditioning system, epoxy or self etch primer



## Mixing Directions

7355 TO VOC Compliant Thinner  
2 Parts                      3 Parts



## Application

Apply 2-3 wet coats, allowing a 10-15 minute flash between coats at 77°F.

**Important Note:** Galvanized steel, bare metal and aluminum are required to be properly cleaned, sanded and treated prior to applying any primer surfacer. To obtain maximum performance always treat bare metal with a quality metal conditioning system.



## Dry Times

TO FLASH	5-10 MINUTES
TO SAND	30 MINUTES
TO TOPCOAT	30 MINUTES



## Recoating

Recoat after a 30 minute dry @ 77° F. Surface must be sanded before recoating.



# HS Acrylic Lacquer Primer



### Pot Life

Indefinite.



### Personal Protection

See product SDS.



### Technical Data

Mixing Ratio: 2:3

Viscosity (RTS): 18 - 20 seconds #2 Zahn

Weight Solids (RTS): 20.58% - 27.09%

Volume Solids (RTS): 9.22% - 13.41%

Film Build: 0.8 mils per full wet coat

Coverage: 151 - 202 sq. ft. per gallon @ 1 dry mil

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
7350	4.5	542	4.2	502
7355	4.8	573	3.7	446
VOC Compliant Reducer	0.0	0	0.0	0
V.O.C. (RTS):				
7350/VOC Compliant Reducer	4.5	542	1.7	201
7355/VOC Compliant Reducer	4.8	573	1.5	178

Disposal/Safety: See MSDS for this product

Humidity Resistance: Excellent

Salt Spray Resistance: Excellent

### SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

**NOTE:** High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will affect dry times and product performance characteristics.