



Description

- 9900 - PERFORMANCE GLOSS ENAMEL - WHITE
- 9901 - PERFORMANCE GLOSS ENAMEL - BLACK
- 9902 - PERFORMANCE GLOSS ENAMEL - SEMI-GLOSS BLACK
- 9903 - PERFORMANCE GLOSS ENAMEL - FLAT BLACK

High Teck's Performance Enamel is a high-solids formula that offers a tough, rust-inhibiting coating with maximum performance. This paint is great for indoor or outdoor use, resists chipping/peeling/fading, hides well, and dries to the touch in as little as 5 minutes. Resistant to heat & gasoline, this coating adheres well to metal, fiberglass, and more. For maximum protection, surfaces should be primed with the High Teck's 9970 Self-Etching primer or 9971 Sandable primer.



Suggested Uses

Wood	Home	Industrial
Metal	Automotive	Construction



Dry Times at 72° F

To Touch: 5 MINUTES
Tack Free: 30 MINUTES
Humidity: 50%
Thickness: 1.5 MIL



Recoating

Curing/Recoat time is extended with multiple coats and excessively thick coats.



Technical Data

Coverage:	Up to 15 square feet
Cleanup:	Paint thinner or lacquer thinner
Flash Point:	-4° F
Specific Gravity:	0.82
Solids Content:	18%
MIR Value:	Glosses: 0.93, cannot exceed 0.95; Flats: 0.74, cannot exceed 0.80
HAPs Content:	Glosses: 10%; Flats: 13%
Storage Temperature:	40° - 100° F
Application Temperature:	50° - 90° F
Abrasion Resistance:	Good
Gasoline Resistance:	Yes
Heat Resistance:	300° F
Resin System:	Chain Stopped alkyd
Shelf Life:	Guaranteed for 2 years
Prop 65:	Yes
Gloss:	High Gloss >80; Semi-Gloss 20-30; Flat <15 (as measured on a 60 degree gloss meter)

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

NOTE: High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will effect dry times and product performance characteristics.