



Description

9971 - PERFORMANCE SANDABLE PRIMER

High Teck's 9971 Performance Sandable Primer is a professional-grade formula specifically designed to meet the performance needs of body shop pros. The large fan actuator eliminates the need for a spray gun on small repair jobs, and also reduces cleanup time. Sandable in 5 minutes, this primer adheres extremely well to bare metal surfaces and offers quality protection against rust and corrosion.



Suggested Uses

Body Panels	Aviation Parts
Engine Parts	Heavy Machinery
Metal Structures	



Dry Times at 72° F

To Touch: 5 MINUTES
Sandable: 5 MINUTES
Humidity: 50%
Thickness: 1.5 MIL



Recoating

Curing/Recoat time is extended with multiple coats and excessively thick coats.



Technical Data

Coverage:	Up to 18 square feet
Cleanup:	Paint or lacquer thinner
Flammability:	Extremely Flammable
Flash point:	-4° F
Specific Gravity:	0.78
Solids Content:	17%
MIR Value:	0.60, cannot exceed 0.70
HAPs Content:	3%
Storage Temperature:	40° - 100° F
Application Temperature:	50° - 90° F
Topcoat:	10 minutes
Gasoline Resistance:	No
Heat Resistance:	250° F
Resin System:	Nitrocellulose lacquer
Shelf Life:	Guaranteed for 2 year
Gloss:	Flat, <15 (as measured on a 60 degree gloss meter)

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

NOTE: High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will effect dry times and product performance characteristics.