



Description

9983 - PERFORMANCE PAINTABLE RUBBERIZED UNDERCOAT

High Teck's Paintable Rubberized paintable undercoating is a great solution for all vehicle undercarriages. The flexible material forms a rubberized skin that reduces road noise and protects metal from salt corrosion, road debris and more. This premium aerosol dries quickly, does not sag, and does not "bleed-thru" when top-coated. VOC compliant.



Suggested Uses

Panel & fender undersides	Weld joints
Hoods & decks	Rust holes
Trunk interiors	All chassis parts
Section repairs	



Dry Times at 72° F

To Touch: 10 MINUTES
To Handle: 6 HOURS
Humidity: 50%
Thickness: 1.5 MIL



Recoating

Curing/Recoat time is extended with multiple coats and excessively thick coats.



Technical Data

Flammability:	"Extremely Flammable"
Flash Point:	-2.2°F
Specific Gravity:	0.80
Solids Content:	~60%
VOC Content:	~23.5%, cannot exceed 40%
MIR Value:	~0.99
HAPs Content:	18%
Storage Temperature:	40-90°F
Application Temperature:	50-100°F
Durability:	Very Good
Abrasion Resistance:	Very Good
Heat Resistance:	300° F
Gasoline Resistance:	No
Resin System:	Petroleum Asphalt
Shelf Life:	Guaranteed for 2 years
Gloss:	Low Lustre, 15-25 (as measured on a 60° gloss meter)

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

NOTE: High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will effect dry times and product performance characteristics.