



Description

7000-1 MULTI-PURPOSE CLEARCOAT
7005-4 MULTI-PURPOSE CLEARCOAT ACTIVATOR - FAST
7006-4 MULTI-PURPOSE CLEARCOAT ACTIVATOR - MEDIUM
7007-4 MULTI-PURPOSE CLEARCOAT ACTIVATOR - SLOW

**Insert
Product
Image Here**

7000 Multi-Purpose Clearcoat has excellent performance and appearance at an economical price. 7000 Multi- Purpose Clearcoat flows out to a smooth, durable finish with excellent gloss.



Surface Preparation

Allow basecoats sufficient dry times.



Mixing Directions

7000 7005/7006/7007
4 Parts TO 1 Part



Application

Apply 2-3 medium wet coats at 35-40 psi or (8-10 psi at the gun when using HVLP), allowing a 10-15 minute flash between coats at 77°F.



Bake Times

FLASH TIME @ 77° F 15 MINUTES
BAKE TIME @ 140° F 30 MINUTES

Allow a 1 to 2 hour cool-down time before wet sanding or buffing after force drying.



Dry Times AT 77° F

DUST FREE 15 MINUTES
TACK FREE 30 MINUTES
TO DELIVER 18 - 24 HOURS
TO BUFF 18 - 24 HOURS



Pot Life @ 77° F

Pot life is 1-2 hours.




Fisheye Eliminator
Not recommended.



Suitable Substrates
Existing OEM Finishes
Refinishing Basecoats



Personal Protection
See product SDS.



Technical Data
Mixing Ratio: 4:1
Viscosity (RTS): 16 - 18 seconds #2 Zahn
Weight Solids 32.21%
Volume Solids: 25.59%
Film Build: 1.0 - 1.5 mils per full wet coat
Coverage: 393 sq. ft. per gallon @ 1 dry mil

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	VOC in LBS./GAL.	Material VOC in G./L.
7000	4.4	522	2.8	331
7005	4.8	569	4.8	469
7006	4.8	570	4.8	570
7007	4.3	521	4.3	521
V.O.C. (RTS):				
7000/7005	4.4	531	2.8	336
7000/7006	4.4	531	2.8	336
7000/7007	4.3	516	2.7	326

Disposal/Safety: See SDS for this product
Humidity Resistance: Excellent
Salt Spray Resistance: Excellent

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

NOTE: High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will affect dry times and product performance characteristics. Check with all State, local and National rules for compliance before use.