



### Description

#### 9970 - PERFORMANCE SELF ETCHING PRIMER

High Teck's 9970 Performance Self-Etching Primer preps bare metal, aluminum and other surfaces to promote adhesion & ensure a smooth topcoat. This corrosion-resistant basecoat is chromate-free and is designed to handle the challenges of seacoast exposure. Great for use with all types of topcoats, including two component (2K) epoxies.



### Suggested Uses

Can be used as an aviation primer on aluminum hulls and parts

Truck and automotive fleets

Marine and Industrial industries where resistance to corrosion is a must

Ideal for spot repair of damaged coatings

Excellent for both aluminum and ferrous metals



### Dry Times at 72° F

To Touch: 10 MINUTES

To Recoat: 30 MINUTES

Hard Cure: 48 HOURS

Humidity: 50%

Thickness: 1.5 MIL



### Recoating

Curing/Recoat time is extended with multiple coats and excessively thick coats.



### Technical Data

Coverage:	Up to 15 square feet
Cleanup:	Paint or lacquer thinner
Flammability:	Extremely Flammable
Specific Gravity:	0.82
Solids Content:	18%
MIR Value:	Does not exceed 0.70
HAPs Content:	11%
Storage Temperature:	40° - 100° F
Application Temperature:	50° - 90° F
Heat Resistance:	350° F
Resin System:	Synthetically modified proprietary resins
Shelf Life:	Guaranteed for 2 years
Gloss:	Flat, <5 (as measured on a 60 degree gloss meter)

#### SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.

**NOTE:** High Teck products are not recommended for use in temperatures below 65°F. Using High Teck products below these temperatures will effect dry times and product performance characteristics.