



POT LIFE

Pot life will be 8-10 hours at 77° F.



FISH EYE

The use of fish eye eliminator is strongly discouraged.

PAINTING FLEXIBLE PARTS

A flexible additive is not required



EQUIPMENT CLEAN-UP

Clean equipment immediately after use with gun wash or a high quality lacquer thinner.



TECHNICAL DATA

Mixing Ratio: 2:1
Viscosity (RTS): 20 - 25 seconds #2 Zahn
Weight Solids 48.98%
Volume Solids: 42.05%
Film Build: 1.0 - 1.2 mils per full wet coat
Coverage: 674 sq. ft. per gallon @ 1 dry mil

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
77125	4.3	513	4.3	513
77150	3.7	444	3.7	444
77152	3.9	470	3.9	470
77160	3.7	444	3.7	444
V.O.C. (RTS):				
77125/77150	4.1	490	4.1	490
77125/77152	4.2	499	4.2	499
77125/77160	4.1	490	4.1	490

Disposal/Safety: See SDS for this product

Humidity Resistance: Excellent

Salt Spray Resistance: Excellent

NOTE: Products are not recommended for use in temperatures below 60° F. Use below these temperatures will effect dry times and performance. FOR INDUSTRY USE ONLY

Read SDS Before Use

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.